



DATA SHEET

Filter media

Blended 80/20

Blended 80/20

Treatment	-
Use	Pleatable filter media
Composition	80% Cellulose + 20% Polyester
Area weight	125 g/m ²
Thickness	0.33 mm
Air Permeability	684 m ³ /m ² /h at 200 Pa
Surface electrical resistance (Ohm)	-
IFA/BIA certificate (DIN EN 60335-2-69:2015)	L
Temperature (dry heat)	
Continuous	80 °C
Peaks	90 °C
Chemical resistance	
Oil/Water	Fair
Hydrolysis	Fair
Acid	Fair
Alkali	Fair
Dust release	Very Good

Order online

shop.Donaldson.com

Contact us

Donaldson.com

Publication DOCAM06618N • Rev. 01 • 0319

Donaldson reserves the right to change or discontinue any model or specification at any time and without notice. Freedom from patent restrictions must not be assumed.