



Donaldson
FILTRATION SOLUTIONS

DATA SHEET

Filter media

Polyester Food

Polyester Food

Composition	100% Polyester Spun Bonded media
Area weight (DIN 53884)	265 g/m ²
Thickness (DIN 53885)	0.7 mm
Air Permeability (DIN 53887)	465 m ³ /m ² /h at 200 Pa
Surface finish	N/A
Additional treatments	N/A
Surface electrical resistance (DIN 54345)	N/A
IFA/BIA certificate (DIN 660335-2-69)	M
Temperature (dry heat)	
Continuous	130 °C
Dust release properties	Very good
Food grade conformity	EU Regulation 10-2011 and FDA 21 CFR 176.170
Application field	Most industrial processes. Applications in the chemical, pharmaceutical and food industry. Shot blasting and powder paint applications as well as other applications in the metal industry. The media is suitable for coarse and fine dust.

Order online

shop.Donaldson.com

Contact us

Donaldson.com

Publication DOCAM083660F • Rev. 00 • 1219

Donaldson reserves the right to change or discontinue any model or specification at any time and without notice. Freedom from patent restrictions must not be assumed.