



Donaldson.
FILTRATION SOLUTIONS

DATA SHEET

Filter media

Sintered Polyethylene

Sintered Polyethylene

Appearance	White
Use	Sintamatic sintered tubes
Composition	Sintered polyethylene composite material
Area weight	1.8 kg/m ²
Thickness	3.5 mm
Area weight	1.8 kg/m ²
Air Permeability (DIN 53887)	1.05 m ³ /m ² /min@200Pa
Surface finish	PTFE membrane
Surface electrical resistance (BGR 132)	N/A
IFA/BIA category (DIN 660335-2-69)	Class M
Temperature (dry heat)	
Continuous	-20 to +70 °C
Peaks	up to 75 °C
Chemical resistance	
Hydrolysis	Excellent
Acids	Very good
Oxidising agents	Good
Abrasion resistance	Excellent
Supports combustion	Yes
What to avoid	Can be degraded by strong oxidising agents such as nitric acid, bromine or chlorine etc. Some organic solvents such as toluene may cause swelling. Avoid very cohesive, sticky materials or moisture sensitive dusts which are likely to crust on the media surface. Also avoid those materials containing oils, fats and greases, etc.
Suitable applications	Sintered elements are suitable for the vast majority of chemical conditions likely to be encountered in Sintamatic applications. Any dust handled should be dry and free flowing, free from any oils, fats or greases etc.

Order online



shop.Donaldson.com

Contact us

Donaldson.com

Publication DOCAM0833301 • Rev. 00 • 1118

Donaldson reserves the right to change or discontinue any model or specification at any time and without notice. Freedom from patent restrictions must not be assumed.